

Parafor 30 GS

Product Ref: (DsB9-0209)
Issue No: 02-1112



MINERAL-SURFACED SBS ELASTOMERIC BITUMEN ROOFING MEMBRANE

DESCRIPTION

Parafor 30 GS is a high performance SBS-modified elastomeric bitumen roofing membrane with a surface finish of mineral flakes or granules and is for application by the torch-on method.

USE

Parafor 30 GS is intended as a cap sheet in a multi-layer system for use in the waterproofing of non-accessible roofs on all roof decks and all roof slopes.

COMPOSITION

Reinforcement:	180 g/m ² non-woven polyester
Bitumen:	SBS-modified elastomeric bitumen
Surface:	Mineral flakes or granules
Underside:	Macro perforated thermo-fusible film

NOMINAL DIMENSIONS AND WEIGHT

Rolls:	8 m x 1 m		
Thickness at selvedge (nominal):	3 mm		
Thickness on main area (nominal):	4 mm		
Selvedge width (+10 mm):	90 mm		
Weight according to surfacing:	Dark grey:	4.6 kg/m ²	36.8 kg/roll
	Granules:	5.0 kg/m ²	39.5 kg/roll

Parafor 30 GS

Product Ref: (DsB9-0209)
Issue No: 02-1112

PHYSICAL CHARACTERISTICS (AVERAGE VALUES)

Tensile strength at break:	> 800 x 600 N/50 mm
Elongation at break:	40 x 45 %
Nail tear resistance:	250 x 250 N
Cold pliability (UEAtc):	< -20° C
Static puncture resistance:	20 kg
Dynamic puncture resistance:	10 mm

Where two values are given, the first is for the longitudinal direction and the second is for the transverse direction.

APPLICATION

Fixing is generally in accordance with BS 8217: 2005 and BS 8000: Part 4: 1989 using the torch-on method.

Parafor 30 GS is fully bonded by torching to a suitable under layer with side laps determined by the selvedge (minimum 80 mm) and minimum 150 mm end laps. At end laps, it is essential to work the granules into the bitumen coating to ensure a homogeneous and watertight bond.

Contact Langley Waterproofing Systems Ltd for detailed specifications and fixing instructions.

COLOURS

Available in; Dark Grey (No. 30)* as standard.

Light Grey (No.1)*, White (No. 2), Brick Red (No. 45), Brown (No. 46),
Brick Orange (No. 48) and Light Green (No. 64) are available to order.

** These colours are mineral flakes. All other colours are granules.*

STORAGE

Parafor 30 GS should be stored on end, under cover, on a firm dry base and away from sources of heat.

SAFETY

This product is not classed as hazardous.

This document is only a guide.

Langley Waterproofing Systems Ltd reserves the right to change the composition and fixing recommendations of products as a result of the evolution of knowledge and technology.